

# Product Data Sheet

## SIDISTAR® R300

### 1. Product Description

SIDISTAR® R300 is a specially designed grey-coloured process modifier consisting of spherical, submicron particles of amorphous silicon dioxide. The nature of the product allows excellent dispersion of these particles in the elastomer matrix. This leads to improved dispersion of all compound ingredients and a better flow, allowing higher extrusion speeds and smoother surface of the end product. The product is supplied in a densified, free flowing, form.

### 2. Application

SIDISTAR® R300 has been designed for usage in dark rubber compounds. Areas of use include flame retardant cable compounds; anti-vibration parts; hoses; roofing membranes; conveyor belts etc.

### 3. Packing

The product is available in big bags as well as in LDPE small bags.

Description	Big Bags	Small Bags
Bags on pallet	1 big bag	50 small bags
Net weight 1 bag	850 kg	20 kg
Net weight on pallet	850 kg (1874 lb)	1000 kg (2205 lb)
Gross weight	850 + 20 = 870 kg (1874 + 44 = 1918 lb)	1000 + 20 = 1020 kg (2205 + 44 = 2249 lb)
Bag dimensions (L x W x H)	106 x 106 x 142 cm (41.7 x 41.7 x 55.9 in)	73 x 46 x 20 cm (28.7 x 18.1 x 7.9 in)
Discharge spout Ø: Length:	42 cm (16.5 in) 70 cm (27.6 in)	
Bag material	Coated woven polypropylene fabric	LDPE bag
Cover / protection	LDPE shrink hood	LDPE shrink hood
Pallet	Fumigated wood	Fumigated wood
Pallet dimensions incl bags (L x W x H)	105 x 105 x 143 cm (41.3 x 41.3 x 56.3 in)	120 x 100 x 140 cm (47.2 x 39.4 x 55.1 in)

### 4. Storage Conditions

The product is recommended to be stored in a covered dry place, protected from direct UV light. Recommended storage temperature between +5 °C and +40 °C (+45°F and +104°F). It's important that the minimum temperature is > 5°C (9°F) above the dew point. Recommended relative humidity < 85%.

### 5. Shelf Life

We recommend that the product should be used within 2 years from production date.

### 6. Health, Safety and Environment

The product safety information, as well as REACH information, can be found on our website: [www.sidistar.com](http://www.sidistar.com).

### 7. Additional Information and contact

For further information about SIDISTAR®, a contact list can be found on our webpage [www.sidistar.com](http://www.sidistar.com). You are also welcome to send your questions to us by email: [info@sidistar.com](mailto:info@sidistar.com)

### 8. Test Methods

Material data given in this product specification refer to analysis according to Elkem internal standard test methods, which are available upon request.

### 9. Version / Updates

The information on this product specification may be subject to change. Please check our website [www.sidistar.com](http://www.sidistar.com), for latest updates, and discard all older versions.

**SIDISTAR®**  
 THE INORGANIC POLYMER ADDITIVE

SIDISTAR® is a registered trademark of Elkem ASA.

This product data sheet is property of Elkem ASA and may not without its written permission be used, copied or made available to others. The receiver is responsible for any misuse

Revised September 2018 © Copyright Elkem ASA

## 10. Physical Data and Chemical Properties

<b>Properties</b>	<b>Test Method</b>	<b>Unit</b>	<b>Limits:</b>
<b>SiO<sub>2</sub></b> (Silicon dioxide, amorphous)	ESM-LAB-18	%	96.0 – 99.0
<b>C</b> (Carbon)	ESM-LAB-05	%	≤ 1.50
<b>Fe<sub>2</sub>O<sub>3</sub></b> (Iron oxide)	ESM-LAB-17	%	≤ 0.25
<b>H<sub>2</sub>O</b> (Moisture, when packed)	ESM-LAB-02	%	≤ 0.8
<b>Cu</b> (Copper)	ESM-LAB-17	ppm	≤ 100
<b>Mn</b> (Manganese)	ESM-LAB-17	ppm	≤ 300
<b>Loss on Ignition</b> (L.O.I.) @ 950°C	ESM-LAB-03	%	≤ 1.80
<b>pH-value</b> (fresh)	ESM-LAB-10		6.5 – 8.5
<b>Bulk Density</b> (when packed)	ESM-LAB-08	kg/m <sup>3</sup>	400 - 700
<b>Other Properties</b> (measured on undensified material)		<b>Unit</b>	<b>Typical Values**:</b>
<b>Specific surface area</b> (BET)		m <sup>2</sup> /g	18 - 25
<b>Median particle size</b>		µm	0.15
<b>Specific Gravity</b>			2.2

\*\* Typical values are for indicational use only, values are not part of Elkem Silicon Materials standard analysis.

**SIDISTAR<sup>®</sup>**  
THE INORGANIC POLYMER ADDITIVE

**SIDISTAR<sup>®</sup>** is a registered trademark of Elkem ASA.

This product data sheet is property of Elkem ASA and may not without its written permission be used, copied or made available to others. The receiver is responsible for any misuse  
Revised September 2018 © Copyright Elkem ASA